



Résine : DURABLE (Type Polypropylene PP)

Caracteristiques :

Couleur : Translucide

La résine Durable a été conçue pour simuler le polypropylène (PP). Elle reprend sa forme initiale après de fortes pressions. Cette résine ductile et résistante à l'usure s'utilise pour réaliser des pièces qui doivent se déformer et présenter un aspect lisse et brillant.

- Prototypes de produits de consommation
- Emballage
- Simule le polypropylène
- Charnières



DURABLE FLDUCL01

	METRIC ¹		IMPERIAL ¹		METHOD
	Green ²	Post-Cured ³	Green ²	Post-Cured ³	
Tensile Properties					
Ultimate Tensile Strength	18.6 MPa	31.8 MPa	2.7 ksi	4.61 ksi	ASTM D 638-10
Tensile Modulus	0.45 GPa	1.26 GPa	65.7 ksi	183 ksi	ASTM D 638-10
Elongation	67 %	49 %	67 %	49 %	ASTM D 638-10
Flexural Properties					
Flexural Stress at 5% Strain	4.06 MPa	27.2 MPa	0.59 ksi	3.95 ksi	ASTM D 790-10, Procedure A
Flexural Modulus	0.16 GPa	0.82 GPa	23.4 ksi	119 ksi	ASTM D 790-10, Procedure A
Impact Properties					
IZOD Impact Strength	130.8 J/m	109 J/m	2.46 ft-lbf/in	2.05 ft-lbf/in	ASTM D 256-10, Test Method A
Temperature Properties					
Heat Deflection Temp. @ 0.45 MPa	< 30 °C	43.3 °C	< 86 °F	110 °F	ASTM D 648-07, Method B
	117.0 µm/m/°C	145.1 µm/m/°C	65.0 µin/in/°F	80.6 µin/in/°F	ASTM E831-14

NOTES:

¹Material properties can vary with part geometry, print orientation, print settings, and temperature.

²Data was obtained from green parts, printed using Form 2, 100 µm, Durable settings, without additional treatments.

³Data was obtained from parts printed using Form 2, 100 µm, Durable settings and post-cured with 2.5 mW/cm² of 405 nm LED light for 120 minutes at 60°C.

SOLVENT COMPATIBILITY

Percent weight gain over 24 hours for a printed and post-cured 1 x 1 x 1 cm cube immersed in respective solvent:

Mechanical Properties	24 HR WEIGHT GAIN (%)
Acetic Acid, 5 %	1.3
Acetone	sample cracked
Isopropyl Alcohol	5.1
Bleach, ~5 % NaOCl	< 1
Butyl Acetate	7.9
Diesel	< 1
Diethyl glycol monomethyl ether	7.8
Hydraulic Oil	< 1
Skydrol 5	1.3
Hydrogen Peroxide (3 %)	1
Isooctane	< 1
Mineral Oil, light	< 1
Mineral Oil, heavy	< 1
Salt Water (3.5 % NaCl)	< 1
Sodium hydroxide (0.025 %, pH = 10)	< 1
Water	< 1
Xylene	6.5
Strong Acid (HCl Conc)	distorted